



## Lime Shift 75% (Chameleon)

Chameleon Lime Shift 75% window film has a unique, head-turning style that shifts from green to yellow with a hint of orange. With 75% VLT, it's fully road legal for windscreens, and 80% IR rejection helps keep your cabin cool and comfortable. It reduces glare, blocks harmful UV rays, and adds a sleek, colorful finish without compromising visibility. Ideal for drivers who want standout looks with real heat protection and everyday practicality.

## **Technical Performance Data**

| Calculated on 3mm glass              |     |
|--------------------------------------|-----|
| Natural Light & Glare                |     |
| VLT (Visible Light Transmission)     | 75% |
| Visible Light Reflectance (internal) | n/a |
| Glare Reduction                      | 23% |
| Solar Energy                         |     |
| Transmittance                        | n/a |
| Reflectance                          | n/a |
| Absorption                           | n/a |
| Total Solar Energy Rejected (TSER)   | 62% |
|                                      |     |

| Thermal Energy              |      |
|-----------------------------|------|
| Shading Coefficient         | n/a  |
| Solar Heat Gain Coefficient | n/a  |
| U-Value - (W/m² K)          | 5.8  |
| R-Value - (m² K/W)          | 0.17 |
| Ultraviolet & Infrared      |      |
| UV Rejection                | 99%  |
| IR Rejection                | 80%  |
| Anti Fade Rating (0-100)    | 76   |

| Manufactured Specifications |          |
|-----------------------------|----------|
| Thickness                   | 50 μm    |
| Structure                   | 2 Ply    |
| Composition                 | PET      |
| Warranty                    | 7 Years  |
| Colour                      | Green    |
| Stock Code                  | CHG7590Z |

For Reference Only: Technical specifications can differ between batches.

Dura Vista retains the right to update this information at any time without notice.

## Product Care & Maintenance:

After installation allow 30 – 60 days to cure. Never try to remove bubbles during the curing process. After curing you may clean the windows with soapy water and non-abrasive cloths or sponges and paper towels. Do not attempt to clean the film with chemicals containing ammonia or abrasives.

## **Installation Guidelines**

| Vertical Installation on standard glass surface |   |
|---|---|
| Single Pane Glass                               |   |
| Clear Single Pane                               | ✓ |
| Tinted Single Pane                              | ! |
| Reflective Tinted Single Pane                   | ✓ |
| Thermally Toughened Safety Glass (EN 12150)     | ✓ |
|   |   |

| Double Pane / Double Glazing                |   |
|---|---|
| Clear Double Pane                           | ✓ |
| Tinted Double Pane                          | ! |
| Reflective Tinted Double Pane               | ✓ |
| Gas-Filled Double Pane (Low-E)              | ! |
| External: SATDIP / PVB / Lam. Safety Glass  | ! |
| Internal: SATDIP / PVB / Lam. Safety Glass  | Х |
| Thermally Toughened Safety Glass (EN 12150) | ✓ |

| Safety Guideline Symbols           | Symbol |
|------------------------------------|--------|
| Safe to install                    | ✓      |
| Unsafe to install                  | Х      |
| Caution, will cause thermal stress | !      |

| Safety Performance      |       |
|-------------------------|-------|
| For Internal use only   | ✓     |
| Peel Strength (gr/inch) | >1800 |
| Signal Interference     | 0%    |
| REACH & RoHS Respected  | ✓     |

Guidelines provided are based on a single glass surface up to  $2.5 \, \text{m}^2$  with no single length or width greater than 2 meters.

