DuraVista
Premium Films

Auto & Architectural

NR Premium 20%

Non-Reflective Premium 20% window tinting provides enhanced privacy by blocking visibility from the outside while maintaining a sleek, dark appearance. It reduces glare and UV rays, protecting interiors from fading and heat buildup. The non-reflective nature ensures a consistent look without dark reflections, offering both style and function for cars, homes, or offices. This film is signal friendly and made for internal use.

Technical Performance Data

Calculated on 3mm glass

Natural Light & Glare	
VLT (Visible Light Transmission)	20%
Visible Light Reflectance (internal)	12%
Glare Reduction	72%
Solar Energy	
Transmittance	32%
Reflectance	17%
Absorption	51%
Total Solar Energy Rejected (TSER)	55%

Thermal Energy	
Shading Coefficient	0.56
Solar Heat Gain Coefficient	0.50
U-Value - $(W/m^2 K)$	5.8
R-Value - $(m^2 K/W)$	0.17
Ultraviolet & Infrared	
UV Rejection	99%
IR Rejection	11%
Anti Fade Rating (0-100)	72

Manufactured Specifications	
Thickness	50 µm
Structure	2 Ply
Composition	PET
Warranty	7 Years
Colour	Natural
Stock Code	NRP20

For Reference Only: Technical specifications can differ between batches. Dura Vista retains the right to update this information at any time without notice.

Product Care & Maintenance:

After installation allow 30 – 60 days to cure. Never try to remove bubbles during the curing process. After curing you may clean the windows with soapy water and non-abrasive cloths or sponges and paper towels. Do not attempt to clean the film with chemicals containing ammonia or abrasives.

Installation Guidelines

Vertical Installation on standard glass surface

Single Pane Glass	
Clear Single Pane	✔
Tinted Single Pane	!
Reflective Tinted Single Pane	✔
Thermally Toughened Safety Glass (EN 12150)	✔

Double Pane / Double Glazing	
Clear Double Pane	!
Tinted Double Pane	X
Reflective Tinted Double Pane	✔
Gas-Filled Double Pane (Low-E)	!
External: SATDIP / PVB / Lam. Safety Glass	X
Internal: SATDIP / PVB / Lam. Safety Glass	X
Thermally Toughened Safety Glass (EN 12150)	✔

Safety Guideline Symbols	Symbol
Safe to install	✔
Unsafe to install	X
Caution, will cause thermal stress	!

Safety Performance	
For Internal use only	✔
Peel Strength (gr/inch)	>1800
Signal Interference	0%
REACH & RoHS Respected	✔
Flamability Test Pass ISO 3795	✔

Guidelines provided are based on a single glass surface up to 2.5 m^2 with no single length or width greater than 2 meters.

- 2H scratch reduction layer
- IR layer with heat reduction properties
- Adhesive layer 1 (to bond PET to IR layer)
- Optically clear PET layer (polyester)
- PSA layer (Pressure Sensitive Adhesive)
- Release liner layer

Non - Reflective Premium - 20%